



## U SeaProtect Roll 50 Alu1

### Rolls aluminium faced - density 50 kg/m<sup>3</sup>

ULTIMATE mineral wool provides a unique high-performance profile: It combines safety, comfort and ease of handling.



#### FIRE RESISTANCE

ULTIMATE provides effective fire resistance, but also very good performance in reaction to fire



#### THERMAL INSULATION

Excellent thermal insulation combined with unique efficiency



#### SOUND ABSORPTION

Improved acoustic comfort due to its excellent sound absorption and sound insulation properties



#### LIGHTWEIGHT

Increase insulation - reduce weight  
ULTIMATE combines high fire & thermal performance with very low weight



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES							STANDARD
Thermal conductivity	T	[°C]	10	50	100	150	200	300	400	EN 12667
	$\lambda_{NR}$	[W/(m·K)]	0.031	0.036	0.042	0.050	0.059	0.080	0.109	
Thermal behaviour	T	[°C]	Exposure to temperature up to 400 °C (depends on density) is possible on the unfaced side, but the thickness of the insulating layer has to be correctly dimensioned so that the faced side is exposed to a maximum of 100 °C. From 150 °C on the binder starts to volatilise.							AGI Q 132

CHARACTERISTIC	SYMBOL	UNIT	THICKNESS	VALUES	STANDARD
Sound absorption value	$\alpha_w$	-	50 mm	1.00	-
			60 mm		

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES		STANDARD
Specific thermal capacity	c	kJ/(kg·K)	1.00		ISO 10456
Reaction to fire	-	-	Melting point according to DIN 4102, part 17: $\geq 1000$ °C. Non combustible according to IMO-Resolution MSC.61(67)-(FTP-Code), IMO MSC/Circ. 1120. Homologated for shipbuilding according to EC Type Examination Certificate Nr.: 114.479		DIN 4102-17 IMO-Resolution MSC.307(88)- (FTP-Code 2010)
Chemical behaviour	-	-	Sulphide free.		-
Application field	-	-	Thermal insulation, acoustic insulation and fire protection constructions in shipbuilding.		-
Material	-	-	Mineral wool with quality mark RAL by the Gütegemeinschaft Mineralwolle e.V., unriskey regarding health according to German decree on dangerous substances, decree on prohibition of chemicals and to guideline EU 97/69 Nota Q.		-
Facing	-	-	U SeaProtect Rolls Alu1 are one-sided faced with reinforced aluminium foil		-
Water vapour diffusion resistance factor	$\mu$	-	- 1		ISO 10456
Quality management	-	-	ISOVER is certified according to DIN EN ISO 9001 and DIN EN ISO 14001.		EN ISO 9001 EN ISO 14001 EN ISO 50001

### DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION\*

THICKNESS D [MM]	WIDTH B [MM]
60	1200

\* Further dimensions on request.



### [www.isover-technical-insulation.com](http://www.isover-technical-insulation.com)

The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. Please verify whether our products are appropriate for the concrete application. For further information please contact our Isover sales offices. We deliver only according to our terms of trade and terms of delivery.

SAINT-GOBAIN ISOVER · Tour Saint-Gobain 12 place de l'Iris 92096 La Défense cedex - France